

Stainflux

Root protector for welding of low-alloyed and stainless steels



Stainflux is applied to root side before welding to protect against oxidation. This is the first step in chemically treating steel for welding process.

Specially formulated for TIG welding of low-alloy and stainless steel with a maximum 25% nickel content but can also be used with other welding methods.

- Prevents oxide inclusions
- Protects the root side from oxidation
- Eliminates pore formation
- Prevents burn-through
- Distributes heat evenly underneath the weld
- Chemically helps cleanse the melt of contaminants

Visit [esab.com](https://www.esab.com) for more information.

Industry

- Aerospace
- Pressure Piping
- Pressure Vessels
- Cryogenic

Specifications

Weight	0.5 kg (1.1 lbs)
Appearance	Grey, Powder
Odor	Odorless
PH Value	10
Solubility	Slightly Soluble

Ordering Information

Stainflux, 0.5 kg (1.1 lbs)	2160000100
-----------------------------	------------



ESAB / [esab.com](https://www.esab.com)

