CARBO S- CuSi 3
CARBO T- CuSi 3

International standards

	S = massive wire	T = bare rod
Werkstoff Nr.	2.1461	
DIN 1733	SG – CuSi3	SG – CuSi3
AWS A 5.7	ER CuSi-A	ER CuSi-A

Approvals --- ---

Application notes

High quality alloyed copper wire for welding CuMn, CuSiMn and CuZn alloys (Mig brazing as well). Suitable for cladding cast iron and un- and low alloyed steels. Temperature and corrosion resistant.
Welding thin plates or galvanized plates in the car industry.

Base material

2.0090, 2.0230, 2.0240, 2.0241, 2.026, 2.0360

Mechanical properties of all-weld-metal

(typical values)

Tensile strength R_m N/mm²	Yielding strength $R_{p0,2}$ N/mm²	Impact strength ISO – V J at Rt.° C	Elongination A_5
350	120	60	40%

Hardness

80 HB

Weld metal analysis
(typical, wt %)

Cu	Mn	Sn	Si	Fe	Zn
Base	1,0	0,10	3,0	0,07	0,1

Gas types EN 439

S = massive wire	T = bare rod
I1-I3	I1

Current

		= +				= –				
Diameter	mm	0,8	1,0	1,2	1,6	1,6	2,0	2,4	3,2	4,0

coils, weight

B300 15 kg. 10 kg./ carton

Rev. 000

Statements on composition and application are just for the applier's information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.

Statements on composition and application are just for the applier’s information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.